

### **Amendments to the Claims**

This listing of claims will replace the originally filed claims in the application.

#### **Listing of Claims:**

Claims 1 – 29 (cancelled)

Claim 30 (new):        A composite (M) comprising:

- a)        at least 75 vol% of a mixed electronic/oxygen O<sup>2-</sup> anionic conducting compound (C<sub>1</sub>) chosen from doped ceramic oxides which, at the use temperature, are in the form of a crystal lattice having oxide ion vacancies and more particularly in the form of a cubic phase, fluorite phase, aurivillius-type perovskite phase, brown-millerite phase or pyrochlore phase; and
- b)        from 0.01 to 25 vol% of a compound (C<sub>2</sub>), different from compound (C<sub>1</sub>), chosen from ceramics of oxide type, ceramics of nonoxide type, metals, metal alloys or mixtures of these various types of materials; and
- c)        from 0 vol% to 2.5 vol% of a compound (C<sub>3</sub>) produced from at least one chemical reaction represented by the equation:



in which equation F<sub>C1</sub>, F<sub>C2</sub> and F<sub>C3</sub> represent the respective crude formulae of compounds (C<sub>1</sub>), (C<sub>2</sub>) and (C<sub>3</sub>) and x, y and z represent rational numbers greater than or equal to 0.

Claim 31 (new):        The composite of claim 30, in which the grains of compound (C<sub>2</sub>) have an equiaxed shape with a diameter ranging from 0.1 µm to 5 µm and preferably less than 1 µm.

Claim 32 (new):        The composite of claim 30, in which the volume fraction of compound (C<sub>3</sub>) does not exceed 1.5% and more particularly does not exceed 0.5% by volume.

Claim 33 (new):        The composite of claim 32, in which the volume fraction of compound (C<sub>3</sub>) in the composite tends toward 0.

Claim 34 (new):        The composite of claim 30, in which the volume fraction of compound (C<sub>2</sub>) is not less than 0.1% but does not exceed 10%.

Claim 35 (new): The composite of claim 34, in which the volume fraction of compound (C<sub>2</sub>) does not exceed 5%.

Claim 36 (new): The composite of claim 30, in which compound (C<sub>2</sub>) is chosen from oxide-type materials and preferably from magnesium oxide (MgO), calcium oxide (CaO), aluminum oxide (Al<sub>2</sub>O<sub>3</sub>), zirconium oxide (ZrO<sub>2</sub>), titanium oxide (TiO<sub>2</sub>), mixed strontium aluminum oxides SrAl<sub>2</sub>O<sub>4</sub> or Sr<sub>3</sub>Al<sub>2</sub>O<sub>6</sub>, mixed barium titanium oxide (BaTiO<sub>3</sub>), mixed calcium titanium oxide (CaTiO<sub>3</sub>), La<sub>0.5</sub> Sr<sub>0.5</sub> Fe<sub>0.9</sub> Ti<sub>0.1</sub> O<sub>3-δ</sub> or La<sub>0.6</sub> Sr<sub>0.4</sub> Fe<sub>0.9</sub> Ga<sub>0.1</sub> O<sub>3-δ</sub>.

Claim 37 (new): The composite of claim 30, in which compound (C<sub>2</sub>) is chosen from materials of the nonoxide type and preferably from silicon carbide (SiC), boron nitride (BN), nickel (Ni), platinum (Pt), palladium (Pd) and rhodium (Rh).


Claim 38 (new): The composite of claim 30, in which compound (C<sub>1</sub>) is chosen from oxides of formula (I):



in which:

- a) R<sub>a</sub> represents at least one trivalent or tetravalent atom mainly chosen from bismuth (Bi), cerium (Ce), zirconium (Zr), thorium (Th), gallium (Ga) and hafnium (Hf), and a and b are such that the structure R<sub>a</sub>O<sub>b</sub> is electrically neutral;
- b) R<sub>c</sub> represents at least one divalent or trivalent atom chosen mainly from magnesium (Mg), calcium (Ca), barium (Ba), strontium (Sr), gadolinium (Gd), scandium (Sc), ytterbium (Yb), yttrium (Y), samarium (Sm), erbium (Er), indium (In), niobium (Nb) and lanthanum (La), and c and d are such that the structure R<sub>c</sub>O<sub>d</sub> is electrically neutral; and
- c) in which x is generally between 0.05 and 0.30 and more particularly between 0.075 and 0.15.

Claim 39 (new): The composite of claim 38, in which compound (C<sub>1</sub>) is chosen from stabilized zirconias of formula (Ia):



in which x is between 0.05 and 0.15.

Claim 40 (new): The composite of claim 30, in which compound (C<sub>1</sub>) is chosen from perovskite oxides of formula (II):



in which:

- a) **Ma** represents an atom chosen from scandium, yttrium, or from the families of lanthanides, actinides or alkaline-earth metals;
- b) **Ma'**, which is different from **Ma**, represents an atom chosen from scandium, yttrium or from the families of lanthanides, actinides or alkaline-earth metals;
- c) **Ma''**, which is different from **Ma** and **Ma'**, represents an atom chosen from aluminum (Al), gallium (Ga), indium (In), thallium (Tl) or from the family of alkaline-earth metals;
- d) **Mb** represents an atom chosen from transition metals;
- e) **Mb'**, which is different from **Mb**, represents an atom chosen from transition metals, aluminum (Al), indium (In), gallium (Ga), germanium (Ge), antimony (Sb), bismuth (Bi), tin (Sn), lead (Pb) and titanium (Ti);
- f) **Mb''**, which is different from **Mb** and **Mb'**, represents an atom chosen from transition metals, alkaline-earth metals, aluminum (Al), indium (In), gallium (Ga), germanium (Ge), antimony (Sb), bismuth (Bi), tin (Sn), lead (Pb) and titanium (Ti);

$$0 < x \leq 0.5;$$

$$0 \leq u \leq 0.5;$$

$$(x + u) \leq 0.5;$$


$$0 \leq y \leq 0.9;$$

$$0 \leq v \leq 0.9;$$

$$0 \leq (y + v) \leq 0.9; \text{ and}$$

**w** is such that the structure in question is electrically neutral.

**Claim 41 (new):** The composite of claim 40, in which compound (**C**<sub>1</sub>) is chosen from compounds of formula (IIa):




corresponding to formula (II), in which **Ma** represents a lanthanum atom.

**Claim 42 (new):** The composite of claim 40, in which compound (**C**<sub>1</sub>) is chosen from compounds of formula (IIb):



corresponding to formula (II) in which **Ma'** represents a strontium atom.

**Claim 43 (new):** The composite of claim 40, in which compound (**C**<sub>1</sub>) is chosen from compounds of formula (IIc):



corresponding to formula (II) in which Mb represents an iron atom.

**Claim 44 (new):** The composite of claim 40, in which compound (C<sub>1</sub>) is chosen from compounds of formula (IIc):



corresponding to formula (II) in which u = 0, y = 0, Mb represents an iron atom, Ma represents a lanthanum atom and Ma' represents a strontium atom.

**Claim 45 (new):** The composite of claim 40, in which compound (C<sub>1</sub>) is a compound of formula:

- a)  $\text{La}_{(1-x-u)}\text{Sr}_x\text{Al}_u\text{Fe}_{(1-v)}\text{Ti}_v\text{O}_{3-\delta},$
- b)  $\text{La}_{(1-x-u)}\text{Sr}_x\text{Al}_u\text{Fe}_{(1-v)}\text{Ga}_v\text{O}_{3-\delta},$
- c)  $\text{La}_{(1-x)}\text{Sr}_x\text{Fe}_{(1-v)}\text{Ti}_v\text{O}_{3-\delta},$
- d)  $\text{La}_{(1-x)}\text{Sr}_x\text{Ti}_{(1-v)}\text{Fe}_v\text{O}_{3-\delta},$
- e)  $\text{La}_{(1-x)}\text{Sr}_x\text{Fe}_{(1-v)}\text{Ga}_v\text{O}_{3-\delta}$  or
- f)  $\text{La}_{(1-x)}\text{Sr}_x\text{FeO}_{3-\delta}.$

**Claim 46 (new):** The composite of claim 45, of formula:

- a)  $\text{La}_{0.6}\text{Sr}_{0.4}\text{Fe}_{0.9}\text{Ga}_{0.1}\text{O}_{3-\delta},$  or
- b)  $\text{La}_{0.5}\text{Sr}_{0.5}\text{Fe}_{0.9}\text{Ti}_{0.1}\text{O}_{3-\delta}.$

**Claim 47 (new):** The composite of claim 40, in which compound (C<sub>1</sub>) is chosen from those of formula (II'):



in which formula (II'):

- a) a, a-1, a'', b, (b+1), (b+β) and b'' are integers representing the respective valences of the Ma, Ma', Ma'', Mb, Mb' and Mb'' atoms; and a, a'', b, b'', β, x, y, s, u, v and δ are such that the electrical neutrality of the crystal lattice is preserved,
- b)  $a > 1;$
- c) a'', b and b'' are greater than zero;
- d)  $-2 \leq \beta \leq 2;$
- e)  $a + b = 6;$
- f)  $0 < s < x;$
- g)  $0 < x \leq 0.5;$
- h)  $0 \leq u \leq 0.5;$

- i)  $(x + u) \leq 0.5$ ;
- j)  $0 \leq y \leq 0.9$ ;
- k)  $0 \leq v \leq 0.9$ ;
- l)  $0 \leq (y + v + s) \leq 0.9$ ;
- m)  $[u (a'' - a) + v (b'' - b) - x + s + \beta y + 2\delta] = 0$ ; and
- n)  $\delta_{\min} < \delta < \delta_{\max}$ ,

where:

$$\delta_{\min} = [u (a - a'') + v (b - b'') - \beta y] / 2 \text{ and}$$

$$\delta_{\max} = [u (a - a'') + v (b - b'') - \beta y + x] / 2, \text{ and}$$

Ma, Ma', Ma'', Mb, Mb' and Mb'' are as defined above, Mb representing an atom chosen from transition metals capable of existing in several possible valences.

Claim 48 (new): The composite of claim 30, in which compound (C<sub>1</sub>) is chosen from oxides of formula (III):



in which:

- a) Mc represents an atom chosen from scandium, yttrium or from the families of lanthanides, actinides and alkaline-earth metals;
- b) Mc', which is different from Mc, represents an atom chosen from scandium, yttrium or from the families of lanthanides, actinides and alkaline-earth metals;
- c) Md represents an atom chosen from transition metals; and
- d) Md', which is different from Md, represents an atom chosen from transition metals, aluminum (Al), indium (In), gallium (Ga), germanium (Ge), antimony (Sb), bismuth (Bi), tin (Sn), lead (Pb) and titanium (Ti); and
- e) x and y are greater than or equal to 0 and less than or equal to 2 and w is such that the structure in question is electrically neutral.

Claim 49 (new): The composite of claim 48, in which compound (C<sub>1</sub>) is of formula (IIIa):



a compound of formula (IIIb):



and more particularly a compound of formula (IIIc):



## REMARKS

Prior to the initial examination of the present application, Applicants wish to have this amendment entered. While adding no new subject matter to the application, Applicants have converted the European style of multiple dependent claims to the U.S. format of single dependency.

Given the above amendments to the claims and the comments herein, Applicants respectfully request notice of allowance of all pending claims at the earliest convenience. However, should the Examiner envision further rejection or comment, he is invited to telephone the undersigned.

Respectfully submitted,

Date: **April 28, 2006**

  
\_\_\_\_\_  
Linda K. Russell, Reg. No. 34,918

Air Liquide  
2700 Post Oak Blvd., 18<sup>th</sup> Floor  
Houston, TX 77056  
Phone: 713-624-8956  
Fax: 713-624-8950

EXPRESS MAIL NO: EV 856933901 US